

STEEL PLUS GLOSS WHITE

Water Based Epoxy Enamel

20-202A USDA White

DESCRIPTION	4 to 1 mix Gloss Water Base Epoxy Enamel (see page 3 for available sizes)
USES	A tough, heavy duty epoxy enamel designed for maximum performance in severe environments. Can be used in immersion applications.
APPEARANCE	Glossy Enamel
RECOMMENDED PRIMERS	Prime Solution 5250 Red / 5253 Gray, Steel Plus P Epoxy primer
PHYSICAL PROPERTIES	
WEIGHT PER GALLON	10.4 lbs.
SOLIDS BY WEIGHT	53%
SOLIDS BY VOLUME	41%
RECOMMENDED DFT	2.5 mils
INDUCTION TIME	NONE
WET FILM TO ACHIEVE DFT 6 mils	
THEORETICAL COVERAGE	
@ 1 Mil DFT	690 sq. ft./gallon
PRACTICAL COVERAGE	265 sq. ft./gallon
@ RECOMMENDED DFT	
(Assumes 15% material loss)	
DRY TIMES @ 70°F - 80°F	Tack Free 1 hour
(21° - 27°C) AND 50% RH	Handle 3-6 hours
	Recoat 2 hours
	Fully Cured 7 days (rate can be accelerated)
POT LIFE	5 + hours with no reduction of gloss
DRY HEAT RESISTANCE	300° F
SHELF LIFE	2 years
PACKAGING	See page 3

SURFACE PREPARATION

All Surfaces: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with BC-4000 cleaner or other suitable cleaner. Thoroughly cured old coatings or new may require scuff sanding for maximum adhesion.

Severe exposures: Abrasive blast to SSPC-SP-10 near white blast before priming
Moderate exposures: Abrasive blast to SSPC-SP-6 commercial blast before priming

APPLICATION

Apply only when air and surface temperatures are between 50°F and 100°F and surface temperature is at least 5°F above the dew point.

THINNING

ROLLER/BRUSH	Use as mixed. Thin with water as needed.
AIR-ATOMIZED SPRAY	Use as mixed. Thin with water as needed.
AIRLESS SPRAY	Normally not needed.
CLEANUP	Soap and water.

EQUIPMENT RECOMMENDATIONS

BRUSH	Quality synthetic bristle brush
ROLLER	Use good quality roller cover.
AIR ATOMIZED SPRAY	Follow equipment manufacturers nozzle and needle selection recommendation for use with medium viscosity paints. Spray at 40- 60PSI.
AIRLESS SPRAY	1800 - 2400 psi with a .013 to .015 tip.
HOT SPRAY	120°F

SAFETY INFORMATION

VOC	1.42 # / gallon or 170 g/l
FLASH POINT	N/A

WARNING: California Prop. 65 warning: Detectable amounts of chemicals known to the state of California to cause cancer, birth defects or other reproductive harm, may be found in this product or its vapors.

For specific information refer to the **Material Safety Data Sheet**.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN

PRODUCT ORDERING INFORMATION:

	<u>Product Number</u>	<u>Size</u>	<u>Wt./Case</u>	<u>Case Quantity</u>
USDA White	20-202A	Gallon	43	4
USDA White	20-202A	5 Gallon	54	1

BURKE INDUSTRIAL COATINGS

600 S. 74th Place, Suite 108, Ridgefield, WA 98642
 Tel: (360) 887-8819 Fax: (360) 887-8825
 Customer Service (800) 348-3245

20-202A Steel Plus Epoxy White and activator 16-Cure

GALLONS (4 TO 1 Mix)							
Total Liquid Gallons	Qty	20-202A		Qty	16-Cure	Qty	16-Cure
	1 1/4	1	F1		1	F4	
2 1/2	2	F1		2	F4		
3 3/4	3	F1		3	F4		
5	4	F1		1	F1		
6 1/4	5	F1		1	F1	1	F4
7 1/2	6	F1		1	F1	2	F4
8 3/4	7	F1		1	F1	3	F4
10	8	F1		2	F1		
11 1/4	9	F1		2	F1	1	F4
12 1/2	10	F1		2	F1	2	F4

QUARTS (4 to 1 Mix)							
Total Liquid Quarts	Qty	20-202A		Qty	16-Cure	Qty	16-Cure
		1					
	2						
	3						
5	4	F4		1	F4		
	5						
	6						
	7						
10	8	F4		2	F4		
	9						
	10						
	11						
15	12	F4		3	F4		

5 GALLON PAILS (4 to 1 Mix)									
Total Liquid Gallons	Qty	20-202A		Qty	16-Cure	Qty	16-Cure	Qty	16-Cure
	6 1/4	1	F5		1	F1	1	F4	
12 1/2	2	F5		2	F1	2	F4		
18 3/4	3	F5		3	F1	3	F4		
25	4	F5		1	F5				
31 1/4	5	F5		1	F5	1	F1	1	F4
37 1/2	6	F5		1	F5	2	F1	2	F4
43 3/4	7	F5		1	F5	3	F1	3	F4
50	8	F5		2	F5				
56 1/4	9	F5		2	F5	1	F1	1	F4
62 1/2	10	F5		2	F5	2	F1		